

FREE CUTTING STEELS**Applications**

- Free Cutting Steels

Kalite Quality	Malzeme No Material No.	%C	%Si	%Mn	%P	%S	%Pb
11SMNPB30	10.718	0.14 max	0.05 max	0.90-1.30	0.11 max	0.27-0.33	0.20-0.35
11SMN30	10.715	0.14 max	0.05 max	0.90-1.30	0.11 max	0.27-0.33	-
12L14	10.737	0.15 max	0.03 max	0.85-1.15	0.04-0.09	0.26-0.35	0.15-0.35
10S20	10.721	0.07 - 0.13	0.40 max	0.70-1.10	0.06 max	0.15-0.25	0.20-0.35
44SMN28	10.762	0.40 - 0.48	0.40 max	1.30-1.70	0.06 max	0.24-0.33	-